

## DESCRIPTION

Terluran® HI-10 is an medium flow, injection molding grade with very high resistance to impact with excellent heat distortion and suitable for injection molding and extrusion.

## FEATURES

- High toughness
- Very high impact
- Medium flow
- Great mechanical strength and rigidity
- High impact at sub-zero temperatures

## APPLICATIONS

- Injection molding
- Compounding
- Appliance housings
- Lawn & garden components requiring superior toughness

Property, Test Condition	Standard	Unit	Values
<b>Rheological Properties</b>			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm <sup>3</sup> /10 min	5.5
<b>Mechanical Properties</b>			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m <sup>2</sup>	36
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m <sup>2</sup>	14
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m <sup>2</sup>	35
Charpy Notched Impact Strength, -30 °C	ISO 179/1eA	kJ/m <sup>2</sup>	13
Charpy Unnotched, -30 °C	ISO 179/1eU	kJ/m <sup>2</sup>	140
Tensile Stress at Yield, 23 °C	ISO 527	MPa	38
Tensile Strain at Yield, 23 °C	ISO 527	%	2.8
Tensile Modulus	ISO 527	MPa	1900
Nominal Strain at Break, 23 °C	ISO 527	%	9
Flexural Strength, 23 °C	ISO 178	MPa	56
Hardness, Ball Indentation	ISO 2039-1	MPa	74
<b>Thermal Properties</b>			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	90
Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h)	ISO 306	°C	103

# Terluran HI-10

Acrylonitrile Butadiene Styrene (ABS)

## TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	93
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	97
Coefficient of Linear Thermal Expansion	ISO 11359	10 <sup>-6</sup> /°C	80 - 110
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
<b>Electrical Properties</b>			
Dissipation Factor (100 Hz)	IEC 62631-2-1	10 <sup>-4</sup>	54
Dissipation Factor (1 MHz)	IEC 62631-2-1	10 <sup>-4</sup>	82
Relative Permittivity (100 Hz)	IEC 62631-2-1	-	2.9
Relative Permittivity (1 MHz)	IEC 62631-2-1	-	2.8
Volume Resistivity	IEC 62631-3-1	Ohm*m	>10 <sup>13</sup>
Surface Resistivity	IEC 62631-3-1	Ohm	>10 <sup>13</sup>
<b>Other Properties</b>			
Density	ISO 1183	kg/m <sup>3</sup>	1030
Water Absorption, Saturated at 23 °C	ISO 62	%	1.03
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.21
Yellowness Index	DIN 6167	-	15
<b>Processing</b>			
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Melt Temperature Range	ISO 294	°C	220 - 260
Mold Temperature Range	ISO 294	°C	30 - 80
Injection Velocity	ISO 294	mm/s	200
Drying Temperature	-	°C	80
Drying Time	-	h	2 - 4

Typical values for uncolored products

## SUPPLY FORM

Terluran® is delivered as spherical pellets. The bulk density of the pellets is from 0.55 to 0.65 g/cm<sup>3</sup>. Standard Packaging unit: 25 kg PE-bag on palette, shrunk or wrapped with PE film or delivery in silo trucks. PE bags should not be stored outside. In dry areas with normal temperature control, Terluran pellets can be stored for relatively long periods of time without any change in mechanical properties. Under poor storage conditions, Terluran absorbs moisture, but this can be removed by drying.

## PRODUCT SAFETY

No adverse effects on the health of processing personnel have been observed if the products are correctly processed and the production areas are suitably ventilated. For styrene, acrylonitrile and 1,3-butadiene the maximum allowable workplace concentrations must be observed according to the pertaining national regulations. In Germany, the following limit values are valid (Oct. 2002): styrene, MAK-value: 20 ml/m<sup>3</sup> = 86 mg/m<sup>3</sup>; acrylonitrile, TRK-value: 3 ml/m<sup>3</sup> = 7 mg/m<sup>3</sup> and 1,3-butadiene, TRK-value: 5 ml/m<sup>3</sup> = 11 mg/m<sup>3</sup>. According to EU directive 67/548/EWG, Annex I and TRGS 905 (Oct. 2002), acrylonitrile and 1,3-butadiene are classified as carcinogenic, category 2 ('substances which should be regarded as if they are carcinogenic to man') and 1 (substances known to be carcinogenic to man), respectively. Experience has shown that during appropriate processing of Terluran with suitable ventilation the values obtained are well below the limits mentioned above. TRGS 402 (Germany) can be used for determining and assessing the concentrations of hazardous substances in the air within working areas. Inhalation of gaseous degradation products, such as those which may arise on severe overheating of the material or during pumped evacuation, must be avoided. Further information can be found in our Terluran safety data sheets.

## DISCLAIMER

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.